

## PRODUCT DESCRIPTION

Dissolvecrete breaks down the ionic bond in Portland cement, completely dissolving and releasing the hardened cement from any surface to which it is adhered. Dissolvecrete is not a Dangerous good, however as with all chemicals we recommend you wear gloves and eye protection when using this product.

## IMPORTANT

- ALWAYS APPLY DISSOLVECRETE TO A DRY SURFACE AREA!
- DO NOT DILUTE DISSOLVECRETE
- MAKE SURE THE EQUIPMENT AND CONCRETE TO BE REMOVED IS DRY – THIS WILL ALLOW DISSOLVECRETE TO BE DRAWN INTO THE CONCRETE.
- REFER TO TEMPERATURE REQUIREMENTS & TESTING SUGGESTIONS (BELOW) PRIOR TO COMMENCING CLEANING.
- ALWAYS USE PPE AS PER THE MSDS
- SURFACE AND AIR TEMPERATURES: Do not clean when temperatures are below freezing or in the extreme heat of direct sun. Best results are obtained when air and surface temperatures are between 5°C and 27°C. (Make sure the surface to be cleaned is cool to the touch)

**PRE TESTING:** It is recommended you should always test prior to beginning a full scale cleaning operation. Testing should confirm cleaning effectiveness on each type of surface being cleaned. Test also to determine the desired surface contact time and potential for any adverse reactions with application. Allow test panels to dry thoroughly before evaluating the final appearance and results.

## APPLICATION INSTRUCTIONS

- Apply Dissolvecrete using a hand held spray bottle. Working from the bottom upwards, apply a thick coating of foam to the dry cement. The Foam should cling to the surface and not drip off.
- When removing concrete slurry, generally leave Dissolvecrete for 5 – 15 minutes before rinsing.
- When removing set concrete, generally leave Dissolvecrete for 20 – 45 minutes (or longer if the coating is thick).
- Make sure to keep the surface wet with Dissolvecrete. If the Dissolvecrete foam soaks in and starts to leave a powdery surface, reapply to these areas.
- If the surfaces changes to a “cottage cheese” like consistency it should now be ready for hosing off with water pressure. Test a small area with a light rub to make sure that the concrete has softened all the way through to the surface of the equipment.
- Wash away the concrete with water (from the bottom to the top). Normal hose pressure is usually enough however a high pressure water cleaner can be used to rinse off thoroughly.
- Gloves and Eye protection are recommended and wash hands thoroughly after use.

### WARRANTY

Permacolour products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification. The information contained herein is true and accurate to the best knowledge of Permacolour. Since we cannot anticipate all possibilities and conditions under which this information and our products may be used, Permacolour hereby accepts no responsibility and offers no warranty in the case of results achieved by the use of our products or of the safe use and suitability of these products. Permacolour offers our products for sale subject to, and “The Customer” and all users are deemed to have accepted our Terms and Conditions of Sale. We warrant our products to be free of manufacturing defects. If any product is found to be defective and was within storage/shelf life, Permacolour will replace the product at no charge to the purchaser. Permacolour makes no other warranty with regards to our products, either expressed or implied. Whilst any information provided by ourselves, both verbally or written, is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the